

Technical Data Sheet



KB-8701

BPA Free Gloss SF OPV

Product Description

KB-8701 exhibits excellent gloss and dry in a low yellowing OPV. Applications include general purpose, folding carton and labels.

Performance Characteristics

- BPA free
- Made with Swiss Ordinance and Nestle compliant materials
- High gloss
- Low yellowing
- Fast oxidative dry

Physical Properties

Tack:	8.0 – 9.0 @ 90°F / 1200 rpm / 1 minute
Inkometer Stability:	0.5 - 1.0 typical tack rise per minute for 10 minutes
Laray Viscosity:	150 – 200 Poise
Yield Value:	1000 – 1500 dynes/cm ²
Oxidative Dry:	3 hrs max.
Solids:	98-100%

FOR YOUR PROTECTION:

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning uses or applications are only the opinion of Kustom Blending, LLC, and users should make their own tests to determine the suitability of this product for their own particular purposes. However, because of numerous factors affecting results, Kustom Blending, LLC makes no warranty of any kind, expressed or implied, including those of merchantability and fitness for particular purpose, other than the material conforms to applicable current Standard Specifications. Standard Specifications, although current at the time of publication, are subject to change without notice. Please refer to the SDS for additional information.

DATE REVISED: 03/08/2019